



Chitosan: A Versatile Bio Polysaccharide with Potential Applications in the Food Industry

Kanneboina Soujanya ^{a*}, Meduri Swapna Sree ^a,
Butti Prabhakar ^b, T. Supraja ^a and P. Yasaswini ^c

^a Department of Food and Nutrition, Post Graduate and Research Centre, PJTSAU, Rajendranagar, Hyderabad, 500030, India.

^b National Institute of Nutrition, Hyderabad, 500007, India.

^c University of Agricultural Sciences, GKVK, Bangalore, India.

Authors' contributions

This work was carried out in collaboration among all authors. All authors read and approved the final manuscript.

Article Information

DOI: <https://doi.org/10.9734/acri/2024/v24i5729>

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/117883>

Review Article

Received: 27/03/2024

Accepted: 30/05/2024

Published: 07/06/2024

ABSTRACT

Chitin is the first identified, renewable and 2nd most prevalent polysaccharide after the cellulose on the earth. It serves as a primary component of fungi cell walls, exoskeletons of arthropods, insects, molluscs, scales of fish and cephalopod beaks. Chitosan is linear deacetylated polysaccharide form of chitin, composed of glucosamine and N-acetyl glucosamine residues linked by β -1,4 bonds. Network of molecules involved rather than just one polymer, which differ in their size, composition, monomer distribution and these properties influence the physicochemical, technical and biological performance of the polymer. Since 1970, chitosan has attracted various scientific and industrial attention because of its unique macromolecular structure, biodegradability, biocompatibility and its

*Corresponding author: Email: kanneboinasoujanya16@gmail.com;

Cite as: Soujanya, Kanneboina, Meduri Swapna Sree, Butti Prabhakar, T. Supraja, and P. Yasaswini. 2024. "Chitosan: A Versatile Bio Polysaccharide With Potential Applications in the Food Industry". *Archives of Current Research International* 24 (5):520-34. <https://doi.org/10.9734/acri/2024/v24i5729>.

potential intrinsic functional characteristics such as antiviral, active element of the diet for weight loss, anticancer, antifungal activity, antimicrobial properties. Chitosan and its derivatives have a wider spectrum of applications in medicine, pharmacy, agriculture, textiles and food industries. Within the health sector, chitin and its derivatives are employed as functional fibers since they possess prebiotic properties, lower blood LDL cholesterol, improve (ameliorate, enhance) glucose intolerance, boost insulin production, alleviate dyslipidemia, and safeguard gut integrity. These unique and excellent structural properties (qualities, attributes) of chitosan and its derivatives permits chitosan for unlimited food applications.

Keywords: Chitosan; antimicrobial; antioxidant; prebiotic; edible films; crustaceans

1. INTRODUCTION

According to UN predictions, the world population will rise to 9.8 billion by around 2050 and 11.2 billion in 2100 (World Population Prospects, 2019) and it is expected to increase food production by about 60%. "Providing enough food that is safe and sufficient for such a rapidly growing population will be extremely difficult to be achieved with the scarcity of resources and the problems posed by climate change, desertification, and the generation of greenhouse gases. Therefore, food produced from non-traditional sources is expected to increase in the next decades" [1].

"Over past 30 years, there has been increased interest in natural polymers due to adverse effects of synthetic polymers on the health and environment [2]. Chitin and its derivative like chitosan are two biological polymers have found enormous utilisation in the recent times. Chitin is the first polysaccharide identified by man" and it is the 2nd most prevalent biopolymer followed by cellulose on the earth obtained from exoskeleton of insect's cuticles (cockroach, beetle, true fly, ants, brachiopods, scorpions, and worm), invertebrates, marine crustacean shell debris, algae (green and brown algae) and in cell wall of fungi (*Aspergillus niger*, *Mucor rouxii*, *Penicillium notatum*, yeast) [3,2,4-7,1]. "The term chitin comes from the Greek word "chiton" which means tunic or envelope" [8]. "It is a non-toxic, biodegradable polymer with high molecular weight which exhibits outstanding biological and chemical properties, such as biodegradability, biocompatibility, bioactivity, non-toxicity and exceptional adsorption properties. considering these unique properties, chitin can be used in different industrial and biomedical applications" [9-11].

1.1 Chitin and Chitosan

Chitosan is a deacetylated derivative of chitin [12], found less frequently in nature such as in

Mucoraceae fungi [3]. It has a highly organised crystalline structure, nitrogenous, hard, colourless to off-white and inelastic [13,14]. Chitosan is a non-toxic, biodegradable, renewable, and biocompatible polymer made of β -1,4-glucosamine and N-acetyl glucosamine units, with the degree of polymerization (DP) level (polymerisation level) ranging from about 1000 to 3000. [12,2,15-20,14, 21,22]. "As degree of deacetylation is defined as the ratio between glucosamine/N-acetyl glucosamine. Therefore, when the percentage of glucosamine exceeds N-acetyl glucosamine the compound is called chitosan and when N-acetyl glucosamine is higher than glucosamine, where the biopolymer is called chitin" [8]. "The level of deacetylation in both chitin and chitosan ranges between 5-15% and 70-95% respectively, the higher degree of acetylation (DA) of chitin lowers solubility in common solvents" [14,21] and limits its applications. The overall nitrogen content of both chitin and chitosan is ~7% because the deacetylation process does not eliminate the nitrogen from the polysaccharide [23].

"Various degrees of the deacetylation and molecular weights of chitosan have been widely applied in different fields such as potential food preservative of natural origin, bactericidal, antifungal, antitumor agents, drug delivery systems, carriers in DNA, enzyme inhibiting activity, adjuvant for vaccine delivery. It is also applied in food, medicine, agriculture and pharmaceutical industries. The level of extent of deacetylation and functional groups influence the effect of chitosan on bacterial activity" [12]. The global market size of chitosan is anticipated to grow at a CAGR (Compound Annual Growth Rate) of 24.7% between 2020 and 2027. "The market for this sort of polymer is expanding in terms of practical/ commercial applications like biomedical, pharmaceutical, food and cosmetics. Recently, there has been an increased interest in the modification of polymers to extend their applicability; knowledge of the mechanisms

involved in the biological activity of chitosan and its derivatives had a great interest" [3]. "Currently, chitosan and its derivatives have practical applications in the form of solutions, suspensions, particles such as nanoparticles and sponges, beads, resins, spheres, gels/hydrogels, foams, membranes and films, fibres, microscopic threads in many fields" [24].

1.2 History of Chitosan

Charles Rouget was the first person to work on extracted chitosan from mushrooms in the year 1850 [25]. When chitin treated with a concentrated alkaline solution under reflux, he obtained a novel chitine modifiee. After many years in 1890's, Felix Hoppe-Seyler treated the shells of crabs, spiders and scorpions with a solution of KOH at 180°C. He obtained a soluble acid solution product named chitosan. Chitosan chemical structure was determined in 1950s. "The first record of chitosan production date back to 1970 in both countries like Japan and united states, these are the two nations dominate worlds chitosan production. The First identification of the presence of chitosan in fungal species was discovered in the year 1983. Craveiro, Craveiro, and Queiroz established the first records for manufacturing and sales of chitosan in the year1999. As a result of the increased use of natural polymers, there was a rise in interest in chitin and chitosan" [26,5,13,27].

1.3 Sources of Chitosan

The average chitin content of sources is cockroaches (18–38%), krill (34–39%), lobster (16–23%), crabs (25–30%), shrimps (30–40%), butterflies (22–64%), mushroom cell walls (8–43%), yeast (1-3%), *Mucor rouxii* (30%), silkworms (20–44%), mold cell walls (8-27%), and *Choanephora cucurbitarum* fungi (28%) [10,28,1,29]. "During processing of shrimps for human consumption, about 40 and 50% of the total mass is waste and 40% of this waste is chitin. It is uncommon for fishing industry waste to be recycled, and a significant portion of waste biomass is dumped into the environment without any prior processing. A significant portion of the biomass generated from fishing-related activities is thrown into the environment untreated, and recycling it is not a usual practice. The majority of the waste is often disposed of in seawater, which is one of the biggest sources of pollution in coastal areas, with a minor portion being dried and used as fertilizer and animal feed. As a

substitute for traditional waste disposal methods, the use of shellfish waste has thus been able to address environmental issues" [13]. "This is an effort towards achieving a zero-waste food industry, hence benefiting both the economy and the environment" [30].

"The major source of industrial level production of chitin comes from the crustacean shells, which are composed of 30–40% proteins, 30–50% mineral salts and 13–42% of chitin (α -, β -and γ -forms). The α , β forms of chitin are usually found in nature" [13]. In contrast to β -chitin, which has parallel sheets, α -chitin has an antiparallel crystalline structure with extensive hydrogen bonding. The third type of chitin is composed of both α and β -chitin, with α -chitin being the most prevalent type in nature.

"In α -chitin, the crystalline structure is composed of antiparallel sheets with widespread hydrogen bonding, while β -chitin consists of parallel sheets. The third form, γ -chitin is a combination of α and β -chitin with α -chitin being the most abundant in nature" [31,32,29].

1.4 Chitosan Production

"Chitosan is the only natural cationic alkaline polysaccharide [33] made of glucosamine and N-acetylglucosamine monomeric units. Chitin is produced by various chemicals (demineralisation followed by deproteinization) and biological treatments (using enzymes and microorganisms). Decolourisation is most commonly performed to produce colourless pure chitin. A chemical procedure (use of both acids and bases) or partial deacetylation of chitin through hydrolysis by a chitin deacetylase is used to produce chitosan" [4,25,34]. "Certain physicochemical flaws, like protein contamination, uneven deacetylation levels, and molecular weight, affect chemical extraction. These days, chitosan is prepared using microwave irradiation in conjunction with chemical and enzymatic techniques, which speeds up chitosan production" [21]. Chitosan can also be obtained directly from the fungi cell walls [13]. "Compared to crustaceans' chitosan, fungal mycelium has no allergenic marine crustacean protein. It has low inorganic content, for which demineralization is not required when processing" [21]. "Largescale production of chitosan at the industrial level usually follows nonenzymatic way of deacetylation process where R-NHCOCH₃ residue is removed by treating chitin with strong alkali (40-50% NaOH solution) at high temperatures (100°C). When the



Fig. 1a. Production of chitosan from marine waste [26]




Fig. 1b. Deacetylation of chitin to produce chitosan [36]

degree of deacetylation is higher than 50 mol% (expressed as a molar percentage), the biopolymer becomes soluble in acidic aqueous solutions and is called chitosan and behaves as a cationic polyelectrolyte due to the protonation of amine groups in the presence of H^+ ions. Commercial chitosan has a DD of up to 90%. Molecular weight, free amino groups and degree of deacetylation significantly influences the physical, chemical properties and wider application of chitosan. Various degrees of deacetylated and molecular weight chitosanes are commercially available in the market” [4,25,21]. Countries like Japan, Norway, Australia, the USA, Korea, China, Canada, France, the UK, Poland and Germany are the markets for chitin and chitosan. Among all the countries, Japan has the highest market for chitosan [35,24]. Chitosan is extracted from bio-waste by a variety of cost-effective techniques, making it significantly less expensive than other biopolymers [13].

2. PROPERTIES OF CHITOSAN

“Various factors influence the solubility of chitosan such as molecular weight, degree of acetylation, pH, temperature, and polymer crystallinity. Chitosan becomes soluble when around 50% of all amino groups are protonated. Chitosan oligomers are soluble over a wide pH range, from acidic to basic ones. Even at high deacetylation, chitosan with high molecular weight is soluble only in the acidic aqueous media. Lack of solubility at neutral and basic pH has hindered the use of chitosan in some applications under neutral physiological

conditions (i.e., PH 7.4). Therefore, a great number of chitosan derivatives with enhanced solubility have been synthesized. Viscosity can be used to determine the stability of the polymer in solution, which is also influenced by the molecular weight of the polymer and the deacetylation degree” [3]. “The presence of free amino and hydroxyl groups improves the functionality of chitosan and so, it can be modified by various methods such as crosslinking, phosphorylation, Sulphatation, graft copolymerisation, etherification, esterification, and carboxymethylation” [5,37]. Chitin derivatives have high economic value due to their biological activities and applications [13]. “Chitosan is an amino polysaccharide with high nitrogen content, hydrophilicity, crystallinity and high viscosity contains reactive groups for cross-linking and chemical inactivation. It is insoluble in water and organic solvents but soluble in dilute acid solvents, forms salts with organic and inorganic acids, chelating properties, ionic conductivity, film forming ability, adsorption properties and flocculating agent” [5].

2.1 Regulations on Chitosan

Food Drug Administration (FDA) declared chitosan to be generally recognized as safe (GRAS) [4]; [24]. In Japan, it was approved as a food additive in 1983 and in Korea in 1995. In 2011, FDA approved chitosan from *A. niger* can be used in alcoholic beverages as a direct secondary ingredient and in 2013 it was approved by the Food Standards Agency of Australia and New Zealand. FDA also added chitosan from white button mushrooms

Table 1. Commercial sources of chitosan products [7]

| Company | Products |
|--|--|
| Chitosanlab | Crustacean shells and squid pens are used to produce Micronized chitin and chitosan, Chitosan nanoparticles, Chitosan quaternary ammonium |
| Alpha Chitin ChitoLytic | Hermetia illucens larvae, fungi, or krill are the sources of chitosan Crustacean, Mushroom, Chitosan lactate, Trimethyl chitosan and Chitin |
| Chibio Biotech | Agaricus bisporus and niger chitosan, Chitin-glucan, Oyster mushroom chitosan, Carboxymethyl chitosan |
| Polymar ISF Chitin & Marine Products LLP | Crustacean chitosan, Poly Floc (flocculant), Poly Protec (fungicide) Chitin and chitosan from marine wastes, Carboxymethyl chitosan |

as a “generally recognized as safe” (GRAS) material for use in foods and beverages [7,38]. Chitosan is used as a food quality enhancer in several countries [37]. In the United States, Environmental Protection Agency classified chitosan as a preservative and antioxidant substance. National Health Surveillance Agency of Brazil, Agencia Nacional de Vigilância Sanitária approved chitosan as a functional health ingredient in food products (Chitosan-fortified fruit juices and chocolates) [26]. It is also approved by the European authorities as safe for consumption and sold in the form of dietary capsules to assist in weight loss [36,37]. Since 1990’s chitosan has also been approved as a food additive (e.g., noodles, potato crisps, biscuits) in Japan and Korea [35].

3. APPLICATIONS OF CHITOSAN IN FOOD SECTOR

Food safety and quality are fundamental concerns for the food industry and consumers [39]. Chitosan is a safe, non-toxic food additive that has been approved by the US Food and Drug Administration (FDA) for use in human food. It is also halal and kosher certified. The use of chitin and chitosan as ingredients in foods or pharmaceutical products, however, requires standardization of identity, purity, and stability [37]. “In the food and nutrition field, there is an increased demand for chitosan due to the utilisation of chitosan as a nutraceutical/functional ingredient in dietary supplements and as a natural additive with a wide range of applications in food products. Many studies have documented the countless biological activities of chitosan such as antioxidant, antimicrobial, antifungal, anti-inflammatory, wound healing, immunostimulant, and prebiotic benefits” [26]. “In the beverage industry, chitosan is used for clarification, coagulation, deacidification, stabilization, filtration membrane and removal of unwanted substances

during the processing of alcoholic and non-alcoholic beverages” [35].

“Chitin and chitosan products fall within the lowest level of concern for toxicological testing. Being naturally present in living organisms, chitin and its deacetylated derivative chitosan are considered safe. The available literature on chitin and chitosan suggests a low order of toxicity, based on chemical structure and animal studies. Like several high-molecular-weight food polymers of natural origin such as cellulose and carrageenan, chitin and chitosan are not expected to be digested or absorbed from the human gastrointestinal tract. To date, chitosan appears to be clinically well tolerated” [37].

3.1 Nutritional Uses

As chitosan is a non-digestible polysaccharide in the upper gastrointestinal tract, which inhibits the absorption of carbohydrates, fats, cholesterol and promotes faster intestinal transit time. It helps to reduce the risk of chronic diseases by increasing the excretion of saturated fatty acids. Prebiotic potential of chitosan improves the gut microbiota. It is also used as a dietary ingredient to control body weight [26].

3.2 As Dietary Fibre

“Prebiotics are a group of nutrients (non-digestible food ingredient) that are degraded by gut microbiota and stimulates the growth of gut microbes and thus improves host health [41]. In recent years, human gut microbiota plays an important role in the maintenance of human health and control development of many non-communicable diseases. Diet has a great influence on the modulation of microbiota [1]. Chitin and chitosan are also considered as dietary fibres and are also naturally present in the fibrous part of tempeh” [25].




Fig. 2. Applications of chitosan [40]

Table 2. Applications of chitosan in food sector

| S. No. | Applications | Chitosan concentration (g/kg) |
|--------|--|-------------------------------|
| 1. | Antimicrobial edible coating for fruits and vegetables | 2-10 |
| 2. | Antimicrobial packaging films | 5-15 |
| 3. | Fat replacer | 5-20 |
| 4. | Cholesterol reducer | 1-5 |
| 5. | Food thickener and stabilizer | 1-5 |
| 6. | Encapsulation carrier for food additives and flavours | 2-10 |
| 7. | Dietary fibre supplement | 1-5 |
| 8. | Antimicrobial agent | 0.1-1 |
| 9. | Food preservation and shelf-life extension | 1-5 |
| 10. | Nutrient delivery system | 2-10 |
| 11. | Antioxidant delivery system | 1-5 |
| 12. | Clarifying agent for juices and wines | 1-5 |
| 13. | Texture enhancement | 1-3 |
| 14. | Allergen control | 1-3 |
| 15. | Water purification | 1-5 |

“Chitosan extracted from crickets was evaluated for its prebiotic potential and its impact on probiotic and pathogenic gut microbes was studied by in-vitro methods. The different concentrations of (1%, 5%, 10% or 20%) chitosan supplanted media on the growth of probiotic and pathogenic bacteria were evaluated after 6, 12, 24 and 48 h upon incubation at 37°C. it was found that all chitosan concentrations significantly decreased the populations of pathogenic bacteria and increased the populations of probiotic bacteria” [42].

The prebiotic potential of chito-oligosaccharide and its nano/microencapsulation for the production of functional yoghurt was done by [43]. *Bacillus cereus* chitosanase was used to produce chito-oligosaccharide by enzyme hydrolysis. The developed Chito-oligosaccharide has a high degree of acetylation, solubility, prebiotic potential, good antioxidant activity but

least stable in the yoghurt. So, encapsulation of chito-oligosaccharide into nanoparticles (100nm) and microparticle ((850µm) have maintained the chito-oligosaccharide 96.83±1.2 % and 45.09 ± 2.5 % respectively in yoghurt.

4. HYPO-CHOLESTEROLEMIC EFFECT

Chitosan is used as an additive to reduce blood, liver triglycerides and cholesterol by binding with lipids. It interferes with the digestion, absorption of fat, lipid metabolism, bile acid synthesis, pancreatic lipase activity and anti-inflammatory effect, binds with micelle and bile acids in the small intestine and forms an insoluble gel-like substance which is excreted in the faeces. It may also chelate cholesterol from food and inhibits food absorption [44,1]. One animal study found that faecal fat excretion was approximately 7.5 times higher in the chitosan fed group compared to that of a cellulose-fed group [45].




Fig. 3. Cholesterol adsorption of chitosan in gastrointestinal tracts [45]

“An edible low-calorie pseudo-fatty-rich meal was prepared by different formulations of chitosan and pectin to standardise a stable preparation with acceptable physical characteristics. A formulation containing 1% chitosan and 6% pectin was best acceptable and when fed to rats resulted in reduced body weight, food and water intake and reduced faecal excretion in the emulsion-administered rats” [46].

4.1 Applications in Food Industry

4.1.1 As an additive in bakery products

Water-soluble chitosan extracted from green mussel by H_2O_2 was used as a fat binder in cookies by [47]. The study found that the addition of this chitosan found no effect on the sensory, protein, moisture or carbohydrate content of cookies, but it showed a significant on the ash and fat content. In all the cookies chitosan binds to fat in liquified butter and peanut oil used during the preparation of cookies.

The chitosan derivative such as succinyl chitosan (2g/100g) was used to replace different levels of fat in cakes. The study found that chitosan replaced cakes have the same density, crumb structure and texture to that of full fat cakes. During staling, chitosan derivative reduced the hardening rate of cakes containing half fat, although drying rate was accelerated [48].

4.1.2 As a functional additive in meat and meat products

“Due to antimicrobial and antioxidant properties, chitosan is used as an additive in flesh foods to control microbial growth, flavour loss, oxidation

and extended shelf life. N-carboxymethyl chitosan (NCCM) and its acetate and lactate derivatives are effective in controlling oxidation and off-flavour development in cooked meat stored at refrigerated temperatures. A study conducted by the US Department of Agriculture found that NCCM is useful as a preservative in flesh foods. The use of chitosan is advantageous, as it is nontoxic, colourless and non-allergic. Prior to flash freezing it is used as a glazing compound to prevent oxidation and extends the shelf life of the product. In combination with other additives, it can be used as a preservative and to improve the textural properties of meat” [37].

4.1.3 Chitosan as coating for eggs

It prevents the transfer of moisture and CO_2 from the albumin and improves the shelf life. It prevents weight loss and enhances yolk index values and Haugh unit, indicating improved yolk and albumin quality of eggs respectively. The coated eggs can be best preserved at $25^\circ C$ for up to 5 weeks, which is at least 3 weeks longer than that observed for uncoated eggs. Overall consumer acceptability of coated eggs did not differ from the commercial eggs [49,39].

In a study, 1.5% of chitosan extracted from shrimp skin was tested for its preservative effectiveness in meatballs. The three treatments were given, meatballs without chitosan, meatballs coated with 1.5% of chitosan and meatballs mixed with 1.5% chitosan solution and all samples were tested using organoleptic properties during storage (1, 2, 3, and 4) in a room temperature. The study revealed that 1.5%

of chitosan coating was found effective for preserving meatballs naturally [50].

Different concentration of chitosan (0%, 1%, 1.5%, 2%, and 2.5%) extracted from shrimp skin was studied for its effectiveness as preservative in sausages by [51]. All the five treatments were evaluated for sensory analysis and bacterial count test. The results showed that sausage with 1% chitosan edible film can maintain the quality of the sausages for three days.

“Chitosan glucose complex showed excellent antioxidant activity than glucose or chitosan alone. It has good scavenging hydroxyl and superoxide anion radicals were also very high. The antimicrobial activity of the chitosan glucose complex was similar to chitosan against common food spoilage and pathogenic bacteria such as *E. coli*, *Pseudomonas*, *Staphylococcus aureus* and *Bacillus cereus*. Incorporation of this modified chitosan into lamb meat increased its shelf life by more than 2 weeks during chilled storage and pork cocktail salami to 28 days. Due to its potential antioxidant and antimicrobial properties the chitosan glucose complex can be used as a promising novel preservative for various food formulations” [52].

4.1.4 As an emulsifying agent

Among the food-grade hydrocolloids, chitosan is an excellent emulsifier. It can be used to stabilise oil in water without the addition of any surfactant, which is due to protonated amino groups giving a positive surface charge to the chitosan under acidic conditions. This converts it into an amphiphilic substance that can adsorb bioactive substances at oil/water interfaces, thus facilitating the formation of an emulsion by lowering interfacial tension. The emulsifying capacity of chitosan, however, is highly dependent on its molecular weight and degree of deacetylation [53].

4.1.5 Antimicrobial agent

Antimicrobial resistance is one of the biggest challenges. The World Health Organisation (WHO) recognises the emergence of resistance as a serious global problem. Resistance has developed to most antimicrobial agents and pesticides, thus placing an enormous burden on food security and health systems [31]. Nowadays, there is an increased demand for healthy and safe food with minimal use of synthetic preservatives. Synthetic polymers are

hazardous to the health and environment. And so, many studies are focussing on the development of biobased polymer as an alternative to plastic packaging [54]. “Several food antimicrobial assays and in vitro experiments have confirmed the bacteriostatic properties of chitosan. Covering the surface of food with chitosan coating or with films extended the shelf life of the food to a certain extent by resisting microbial attack and slowing the food spoilage. Chitosan with a high degree of deacetylation and low molecular weight had a better inhibition effect. The three generally accepted theories for the antibacterial properties of chitosan are due to electrostatic interaction between negatively charged groups on the bacterial surface and R-NH³⁺ of chitosan which destabilizes the cell membrane structure, and the leakage of intracellular material leads to microbial death. The second idea pertains to chitosan's ability to chelate metal ions. Meanwhile, the third theory posits that chitosan penetrates cells through DNA binding, influencing RNA transcription and protein expression to provide the inhibitory impact on bacteria” [33,55].

“It is effective against both Gram-positive and Gram-negative foodborne microorganisms, including *Clostridium perfringens*, *Brochothrix spp.*, *Aeromonas hydrophila*, *Bacillus cereus*, *B. licheniformis*, *B. subtilis*, *Enterobacter sakazakii*, *Lactobacillus spp.*, *Listeria monocytogenes*, *Pseudomonas spp.*, *Salmonella typhimurium*, *S. enteritidis*, *Serratia liquefaciens*, *Staphylococcus aureus*, and *Escherichia coli* O157H7; the molds *Aspergillus*, *Penicillium*, and *Rhizopus*; the yeasts *Candida*, *Saccharomyces*, and *Rhodotorula*. The chitosan and its derivatives are effective against plant pathogenic bacteria such as *A. tumefaciens*, *C. fascians*, *E. amylovora*, *E. carotovora*, *P. solanacearum*, and *S. lutea* and fungi *A. alternata*, *B. fabae*, *F. oxysporum*, *P. digitatum*, *P. debaryanum*, and *R. solani*” [37].

In a study, whey protein isolates and chitosan edible films containing 4% Zataria multiflora Boiss essential oil exhibited good microbial activity against *Listeria monocytogenes*, *Bacillus cereus*, *Staphylococcus aureus*, *Escherichia coli* and *vibrio parahaemolyticus* [56].

Chitosan-fructose Maillard reaction products exhibited greater antibacterial activity compared to the original chitosan against *S. aureus* and *E. coli*. It resulted from the chitosan-Maillard products disrupted the microorganism's

membrane integrity, which successfully prevented bacterial cell inactivation because of their positively charged state [57].

5. EDIBLE FILMS, COATINGS AND PACKING

In the last 20 years, there has been an increase in the concentration on improving the safety and sanitation of food production. Packaging plays an important role in the protection of food from physical, chemical and biological hazards. Due to functional properties, convenience and price, plastic packing is widely used. But the use of petroleum-based packaging affects the environment and the health of consumers. So, biodegradable natural polymers widely studied for prospective applications in the food industry are chitosan [58,15].

Due to rising awareness about the side effects of chemical preservatives in food, scientists are looking for new alternate food preservatives. Chitosan is considered as an effective natural preservative due to its functional properties like chelating agent, film forming ability, antimicrobial, antioxidant and binding [59]. Along with protective barrier properties, edible films can also be used as carriers of bioactive compounds to enhance the quality of the food [8].

Chitosan based films are tough, flexible, durable to extension characteristics and exhibit gas (oxygen and carbon dioxide) and aroma barrier activities that are appropriate for food packaging [30,55]. Chitosan has antimicrobial activity against a wide range of foodborne pathogens such as fungi, yeast, and bacteria, being more active against yeasts. It can be used as an alternative to synthetic antioxidant and antimicrobial agents [60,3]. Chitosan films are not applicable for aqueous medium containing small amounts of organic acids like acetic acid and humid conditions. Several studies have been going on to overcome these limitations by using surface modification techniques, combining chitosan with other polymers and adding active substances like essential oils and antimicrobial agents [55].

[61] worked on production of chitosan-based biodegradable active films using bio-waste enriched with polyphenol propolis (PS) extract was investigated [61]. The study found that the addition of PS extract enhanced the film's thermal stability, mechanical properties (tensile modulus, yield strength, and stress at break),

antioxidant and antimicrobial activities. The incorporation of plant polyphenols improves the poor moisture barrier properties of chitosan film, as these antioxidant compounds interact and form bonds with reactive groups of chitosan. Chitosan is used in the production of edible, antimicrobial, intelligent, active, biodegradable films and coatings. The functionality of chitosan-based films and coatings is improved by blending it with other polymers such as polysaccharides, fats and proteins [54].

Effect of edible coating of chitosan-pullulan (50:50) blend enriched with pomegranate peel extract on the quality and shelf life of tomatoes stored at 23 °C and 4 °C for 18 days was studied by [62]. The study found that the edible coating of tomatoes stored at both temperatures have significantly ($p \leq 0.05$) maintained TSS, colour, titratable acidity, pH and retained higher antioxidant activity and sensory quality than the uncoated tomatoes. Overall, the shelf life of tomatoes was increased by 9 days at 23 °C and 4 °C conditions.

The process of coating, which can be done by brushing, electrostatic spraying, or dip coating, involves applying a layer of chitosan solution to the food's surface. Food preservation research frequently makes use of it because of its exceptional operability and convenience benefits [33].

The freshness of foodstuffs is monitored by the intelligent pH indicator films, the change in pH of the food changes the colour of the indicator. By this consumer can see the condition of food. Intelligent pH-indicator chitosan-based films have been extensively studied over the last few years [58].

Effect of coating different concentration (0.5, 1, 2 and 2.5%) of chitosan extracted from shrimp shells on tomato quality was evaluated by [63]. The TSS, pH, titratable acidity, shrinkage and lycopene content of tomatoes were investigated for a period of 30 days at ambient temperatures. Coated tomatoes were firmer, change in pH and TSS was less than the control sample. Control tomatoes deteriorated on the 20th day of storage whereas coated tomatoes delayed ripening and extended shelf life up to 30 days. Among all the treatments 2.5% chitosan resulted in better extension of the shelf life of tomatoes than other treatments.

The chitosan extracted from prawn shell waste was analysed for its preservative potential in

vegetables such as brinjal, tomato and capsicum. The study found that chitosan sprayed vegetables caused delayed ripening and extended shelf life whereas softening of texture was observed in uncoated vegetables at the end 8th day of observation [64].

In a study, different grafting degrees of p-hydroxybenzoic acid-grafted chitosan (PA-g-CS) conjugates synthesized by a free radical-regulated grafting approach were developed into films by casting, and their characteristics and preservative effects on fresh-cut jackfruit were evaluated. Compared to the chitosan film, the PA-g-CS film exhibited excellent performance such as enhancements of water solubility, antioxidation, and antibacterial activity. When compared to the control, application of PA-g-CS films to fresh-cut jackfruit enhanced the quality of products by inhibiting the weight loss, softening, membrane damage and maintenance of TSS, ascorbic acids contents, reduced bacterial count and a higher sensory score. Among these PA-g-CS films, the highest degree of grafting posed the best preservation effect [65].

In a study, nano-chitosan was made with various concentrations of 3:1, 4:1 and 5:1 using ionic gelation and sprayed on fishery products. These three concentrations showed bacterial inhibition and extended shelf life of fishery products. Among three concentrations, 3:1 nano-chitosan was the best treatment. Crab shell-based nano-chitosan spray has good antibacterial activity and preservative effectiveness [66].

“The edible coating of chitosan–pullulan (50:50) composite was prepared with pomegranate peel extract (0.02 g/mL) was coating on the mango fruits stored for 18 days at room (23°C) and cold (4°C) temperature. The study found that application of composite coating extended the shelf life of mangoes at both storage temperatures. The coating reduced the physiological loss, maintained the sensory quality, freshness, TSS, pH, phenolic content and antioxidant activity of mangoes than the control sample” [67].

“Effect of edible coating of chitosan: pullulan (50:50) composite enriched with pomegranate peel extract on the quality, sensory attributes and shelf life of litchi fruit stored period at room and cold temperature for 18 days. The results of the study showed that the application of coating significantly reduced the physiological weight loss, TSS, acidity and browning of litchi fruits

during storage days as compared to control. Coating of the blend significantly increased the shelf life of litchi stored at both temperatures” [68].

5.1 Antioxidant Properties

The chelating activity, denser intramolecular hydrogen bonds of high molecular weight chitosan, -OH and -NH₂ functional groups in chitosan prevent oxidation reactions and exhibit antioxidant activity [33,37,19]. Amino and several hydroxyl groups of chitosan interact with free radicals and exhibit scavenging activity. Some chitosan derivatives such as chitosan sulphates or N-2 carboxyethyl chitosan and Chitoooligosaccharides have improved antioxidant activity due modification of polymer with phenolic or gallic acid compounds [3]. When compared to native chitosan, sulphated and sulfanilamide chitosans exhibited high antioxidant activity which is mainly due to the enhanced water solubility and hence increased availability to free radicals [11].

The chitin was extracted from *Parapenaeus longirostris* shrimp shell waste and chitosan was deacetylated by classical, ultrasound method and analysed for its antioxidant activity. The degree of deacetylation of chitin (CHI), classical deacetylated chitosan (CDC) and (ultrasound-assisted deacetylated chitosan (UDC) exhibited scavenging ability on DPPH radicals ranged from 4.71% to 21.25%, 11.45% to 32.78% and 18.27% to 44.17%, respectively, at the concentrations of 0.25 to 1 mg/mL. The inhibition of lipid peroxidation with TBARS ranged from 11.7% to 51.63%, 17.24% to 63.52% and 29.31% to 77.39%, respectively (0.25 to 1 mg/mL concentration) [69].

5.2 As an Encapsulation Matrix

The material used as an encapsulation matrix must be food grade and should possess particular physical and chemical properties to protect the encapsulated compounds. Chitosan-based microcapsules exhibited a good positive influence on the survival rates of different probiotic bacteria under *in vitro* conditions [71]. Both *L. gasseri* and *B. bifidum* were microencapsulated using prebiotics quercetin and chitosan as coating material in alginate microparticles. It was found that microencapsulated organisms improved survival under *in vitro* conditions [72]. Use of chitosan as coating material and resistant starch as




Fig. 4. Effect of chitosan coating on fruits and vegetables [70]

prebiotics increased the viability of many probiotic bacteria up to 6 months at room conditions [73]. Encapsulation of bioactive compounds with chitosan protects from oxidation. Chitosan (CS) enriched with salicylic acid (SA) treatment significantly maintained texture and colour, inhibited moisture loss and acidity change [38].

5.3 As a Clarification Agent

Chitosan is used as a membrane due to its good mechanical durability, chemical resistance, high selectivity and high permeate rates in membrane technology. Chitosan is used in the treatment of wastewater. As it is used for the removal of colour and metals. It is also used to precipitate/agglomerate compounds during the processing of food wastage [74]. Clarification is an important step to remove pectin and other carbohydrates present in the fruit juice during processing. It can be done by microfiltration or by the use of clarifying agents. Being nontoxic, biodegradable and as a coagulation agent, chitosan was successfully used as a clarifying aid for orange, apple, grape, lemon and bayberry juices, besides wine and green tea [75].

One of the most common defects affecting white wines is browning due to oxidation. It can be reduced by using adsorbents to reduce phenolic compounds. The use of chitosan for clarification

of wine and vinegar exhibits a high affinity to a number of phenolic compounds, particularly cinnamic acid which prevents browning in a variety of white wines [37].

6. OTHER APPLICATIONS

Colour is the important parameter that indicates the freshness and quality of the product. Many foods contain colours naturally and some food colours are enhanced by various pigments and either natural or synthetic colourants. Nowadays there is an increased interest towards natural pigments but these are sensitive to the surrounding atmosphere. Chitosan natural pigment complexes can stabilise the pigments and prevent their decay during storage [25]. Depending upon the degree of deacetylation, chitosan is suitable to be used as a thickener and stabiliser in mayonnaise and peanut butter [25].

The concept of sustainable catalysts has been increased recently. Chitosan-based preparations loaded with metal ions and complexes as well as metal nanoparticles can be successfully used to induce different reactions, enhancing the amount of available and increasing the availability of active sites [74]. Some of the potential health hazards of chitosan include: allergic reactions: gastrointestinal issues, nutrient absorption, interactions with medications, risk of contaminants and long-term safety.

7. CONCLUSION

Chitosan is one of the most emerging materials for various applications. A large amount of the crustacean shell waste as a major by-product of seafood waste can be used in the production of value-added chitin and chitosan. When compared to other biopolymers, the production of chitosan by energy-efficient methods is much cheaper. It has a prominent role in the protection of the plant due to the multiple biochemical activities and variety of inexpensive sources from which can be sustainably obtained. It is an abundantly available and versatile biopolymer with a broad range of applications with numerous merits. With the use of advanced technologies, it can be comfortably moulded into different derivatives according to the end use. Chitosan based degradable membranes in conjugation with other materials have enhanced their scope.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

1. Lopez-Santamarina A, Mondragon AC, Lama A, Miranda JM, Franco CM, Cepeda A. Animal-origin prebiotics based on chitin: An alternative for the future? A Critical Review. *Foods*. 2020;9(782):1-20.
2. Kaczmarek MB, Struszczyk-Swita K, Li X, Szczesna-Antczak M, Daroch M. Enzymatic modifications of Chitin, Chitosan, and Chitooligosaccharides. *Frontiers in Bioengineering and Biotechnology*. 2019;7(243):1-26.
3. Aranaz I, Alcántara AR, Civera MC, Arias C, Elorza B, Caballero AH, Acosta N. Chitosan: An overview of its properties and applications. *Polymers. International Journal of Molecular Sciences*. 2021;22(10968):1-26.
4. Cosme F, Vilela A. Chitin and Chitosan in the alcoholic and non-alcoholic beverage industry: An Overview. *Applied Sciences*. 2021;11(11427):1-18.
5. Jiménez-Gómez CP, Cecilia JA. Chitosan: A Natural Biopolymer with a Wide and Varied Range of Applications. *Molecules*. 2020;25(3981):1-43.
6. Sandeep A, Sangameshwar K, Mukesh G, Chandrakant R, Avinash D. A brief Review on chitosan applications. *Indo American Journal of Pharmaceutical Research*. 2013;3(12):1564-1574.
7. Lárez-Velásquez C. Chitosan: An overview of its multiple advantages for creating sustainable development poles. *Polímeros*. 2023;33(1):1-15.
8. Hamed I, Ozogul F, Regenstein JM. Industrial applications of crustacean by-products (chitin, chitosan, and chitooligosaccharides): A review. *Trends in Food Science & Technology*. 2016;1-45.
9. Rodrigues MR, Silva ADS, Lacerda FV. The chitosan as dietary fiber: An *In vitro* comparative study of interactions with drug and nutritional substances. *The Complex World of Polysaccharides*. Chapter. 2012; 23:603-616.
10. Vedula SS, Yadav GD. Chitosan-based membranes preparation and applications: Challenges and opportunities. *Journal of the Indian Chemical Society*. 2021;98(100017):1-14.
11. Gutiérrez TJ. Chitosan Applications for the Food Industry. *Chitosan*. Chapter. 2017;8: 185–232.
12. Tajdini F, Amini MA, Nafissi-Varchehc N, Faramarzi MA. Production, physiochemical and antimicrobial properties of fungal chitosan from *Rhizomucor miehei* and *Mucor racemosus*. *International Journal of Biological Macromolecules*. 2010;47:180–183.
13. Santos VP, Marques NSS, Maia PCSV, de Lima MAB, Franco LDO, de Campos-Takaki GM. Seafood waste as attractive source of chitin and chitosan production and their applications. *International Journal of Molecular Sciences*. 2020;21(4290):1-17.
14. Cheba BA. Chitin and Chitosan: Marine biopolymers with unique properties and versatile applications. *Global Journal of Biotechnology & Biochemistry*. 2011;6(3): 149-153.
15. Manigandan V, Karthik R, Ramachandran S, Rajagopal S. Chitosan applications in food industry. *Biopolymers for Food Design*. Chapter. 2018;15:467-489.
16. Honarkar H, Barikani M. Applications of biopolymers I: chitosan. *Applications of biopolymers*. 2009;140:1403–1420.
17. Kumari S Kishor R. Chitin and chitosan: Origin, properties, and applications. *Handbook of Chitin and Chitosan*. Chapter. 2020;1:1-33.

18. Alvarenga ES. Characterization and properties of chitosan. *Biotechnology of Biopolymers*. Chapter-5.2014;91-108.
19. Baptista RC, Horita CN, Sant'Ana AS. Natural products with preservative properties for enhancing the microbiological safety and extending the shelf-life of seafood: A review. *Food Research International*. 2020;127(108762): 1-23.
20. Liutkevičius A, Speičienė V, Alenčikienė G, Sekmokienė D, Žvirdauskienė R, Mieželiienė A.. Influence of chitosan on microbiological data and quality characteristics of spreadable curd cheese and mayonnaise. *Veterinarija ir zootechnika (Vet Med Zoot)*. T. 2015;69 (91):38-47.
21. Guan Z, Feng Q. Chitosan and Chitooligosaccharide: The promising non-plant-derived prebiotics with multiple biological activities. *International Journal of Molecular Sciences*. 2022;23(6761):1-18.
22. Kurita K. Chitin and chitosan: Functional biopolymers from marine crustaceans. *Functional biopolymers from marine crustaceans*. 2006;8:203–226.
23. Pal K, Bharti D, Sarkar P, Anis A, Kim D, Chalas R, Maksymiuk P, Stachurski P, Jarzebski M. *Selected Applications of Chitosan Composites*; 2021.
24. Morin-Crini N, Lichtfouse E, Torri G, Crini G. Applications of chitosan in food, pharmaceuticals, medicine, cosmetics, agriculture, textiles, pulp and paper, biotechnology, and environmental chemistry. *Environmental Chemistry Letters*. 2019;1-26.
25. Harkin C, Mehlmer N, Woortman DV, Brück TB, Brück WM. Nutritional and additive Uses of Chitin 2 and Chitosan in the Food Industry. *Sustainable Agriculture Reviews* 36. Chapter-1; 2019.
26. Teixeira-Costa BE, Andrade CT. Chitosan as a valuable biomolecule from seafood industry waste in the design of green food packaging. *Biomolecules*. 2021;11(1599): 1-19.
27. Lizardi-Mendoza J, Monal WMA, Valencia FMG. Chemical characteristics and functional properties of chitosan. *Chitosan in the Preservation of Agricultural Commodities*. Chapter. 2016;1:3-31.
28. Jones M, Kujundzic M, John S, Bismarck A. Crab vs. mushroom: A review of crustacean and fungal chitin in wound treatment. *Mar. Drugs*. 2020;18:64.
29. Yadav M, Goswami P, Paritosh K, Kumar M, Pareek N, Vivekanand V. Seafood waste: A source for preparation of commercially employable chitin/chitosan materials. *Bioresources* ; 2019.
30. Wong JF, Chan JX, Hassan A, Mohamad Z, Othman N. *Composite Materials: Applications in Engineering, Biomedicine and Food Science*. Chapter-21. 2019;431-458.
31. Jardine J, Sayed S. Valorisation of chitinous biomass for antimicrobial applications. *Pure applied chemistry*. 6th International IUPAC Conference on Green Chemistry (ICGC-6), Venice (Italy). 2017; 1-14.
32. Hajji S, Younes I, Ghorbel-Bellaaj O, Hajji R, Rinaudoc M, Nasri M, Jellouli K. Structural differences between chitin and chitosan extracted from three different marine sources. *International Journal of Biological Macromolecules*. 2014;1-9.
33. Liu T, Li J, Tang Q, Qiu P, Gou D, Zhao J. Chitosan-based materials: An overview of potential applications in food packaging. *Foods*. 2022;11(1490):1-18.
34. Premasudha P, Vanathi P, Abirami M. Extraction and characterization of chitosan from crustacean waste: A constructive waste management approach. *International Journal of Science and Research (IJSR)*. 2015;6(7):1194-1198.
35. Hauzoukim Swain S, Ghosh SK, Roy A. Application of chitosan and chitosan derivatives: A review. *The Pharma Innovation Journal*. 2021;10(7):150-155.
36. Martău GA, Mihai M, Vodnar DC. The use of Chitosan, Alginate, and Pectin in the Biomedical and Food Sector—Biocompatibility, Bioadhesiveness, and Biodegradability. *Polymers*. 2019;11 (1837):1-28.
37. Chawla SP, Kanatt SR, Sharma AK. Chitosan. *polysaccharides*. 2014;1-24. DOI. 10.1007/978-3-319-03751-6_13-1
38. Cheba BA. Chitosan: Properties, Modifications and Food Nanobiotechnology. 13th International Conference Interdisciplinarity in Engineering (INTER-ENG 2019). *Procedia Manufacturing*. 2020;46:652–658.
39. Hu Z, Ganzle MG.. Challenges and opportunities related to the use of chitosan as a food preservative. *Journal of Applied Microbiology*. 2018;126:1318-1331.
40. Ahmed S, Ikram S. Chitosan & its derivatives: A review in recent innovations.

- International Journal of Pharmaceutical Sciences and Research. 2015;6(1):14-30.
41. Davani-Davari D, Negahdaripour M, Karimzadeh I, Seifan M, Mohkam M, Masoumi SJ, Berenjian J, Ghasemi Y. Prebiotics: Definition, types, sources, mechanisms, and clinical applications. *Foods*. 2019;8(92):1-27.
 42. Kipkoech C, Kinyuru JN, Imathiu S, Meyer-Rochow VB, Roos N. *In vitro* Study of Cricket Chitosan's Potential as a Prebiotic and a Promoter of Probiotic Microorganisms to Control Pathogenic Bacteria in the Human Gut. 2021;10(2310):1-13.
 43. Ismail SA, El-Sayed HS, Fayed B. Production of prebiotic chitooligosaccharide and its nano/microencapsulation for the production of functional yoghurt. *Carbohydrate Polymers*. 2020;234 (115941):1-11.
 44. Preuss HG, Kaats GR. Chitosan as a dietary supplement for weight loss: A review. *Current Nutrition & Food Science*. 2006;2:297-311.
 45. Gallaher SM, Munion J, Hesslink R, Wise Jr, Gallaher JDD. Cholesterol reduction by glucomannan and chitosan is mediated by changes in cholesterol absorption and bile acid and fat excretion in rats. *Journal of Nutrition*. 2006;130:2753–2759.
 46. Qinna NA, Akayleha FT, Remawi MMA, Kamonaa BS, Tahac H, Badwan AA. Evaluation of a functional food preparation based on chitosan as a meal replacement diet. *Journal of Functional Foods*. 2013;5:1125-1134.
 47. Permadi A, Afifah RA, Apriani DAK, Ariyani F. Water soluble chitosan from green mussel (*Perna viridis*) Shells and Its Use as Fat Absorber in Cookies. *Squalen Bulletin of Marine and Fisheries Postharvest and Biotechnology*. 2022;17(3):168-176.
 48. Rios RV, Garzon R, Lannes SCS, Rossel C. Use of succinyl chitosan as fat replacer on cake formulations. *LWT Food Science and Technology*. 2018;1-26.
 49. Bhale S, No HK, Prinyawiwatkul W, Farr AJ, Nadarajah K, Meyers SP. Chitosan coating improves shelf life of eggs. *J Food Sci*. 2003;68:2378–2383.
 50. Gita RSD, Waluyo J, Dafik, Indrawati. The effectiveness of chitosan from shrimp skin as a natural preservative for meatball. *Journal of Physics: Conference Series*. 2021;1839 (012024):1-10.
 51. Gita RSD, Waluyo J, Dafik, Indrawati. The effectiveness of using chitosan as a natural antibacterial for maintaining the sausage quality. *Food Research*. 2022;6(4):146-153.
 52. Kanatt SR, Chander R, Sharma A. Chitosan glucose complex – A novel food preservative. *Food Chemistry*. 2008;106: 521–528.
 53. Gutiérrez TJ. Chitosan applications for the food industry. *Chitosan*. Chapter. 2017;8: 185-232.
 54. Kumar S, Mukherjeeb A, Dutta J. Chitosan based nanocomposite films and coatings: Emerging antimicrobial food packaging alternatives. *Trends in Food Science & Technology*. 2020;97:196–209.
 55. Luangapai F, Peanparkdee M, Iwamoto S. Biopolymer films for food industries: Properties, applications, and future aspects based on chitosan. *Reviews in Agricultural Science*. 2019;7:59-67.
 56. Gharehbagh SS, Khanjari A, Davaji MY, Basti AA. The use of chitosan and whey protein isolate edible films incorporated with *Zataria multiflora* Boiss. Essential oil as an active packaging ingredient against some common foodborne bacteria. *Journal of Food Biosciences and Technology*. 2017;7(1):41-48.
 57. Yang H, Zhang Y, Zhou F, Guo J, Tang J, Han J, Li Z, Fu C. Preparation, bioactivities and applications in food industry of chitosan-based maillard products: A Review. *Molecules*. 2020;26(166):1-15.
 58. Florez M, Guerra-Rodríguez E, Cazon P, Vazquez M. Chitosan for food packaging: Recent advances in active and intelligent films. *Food Hydrocolloids*. 2022;124 (107328):1-16.
 59. Siddique F, Arshad M, Hassan W, Shah ZH, Akhtar U. A review on Chitosan: As a potent fish preservative. *International Journal of Biosciences*. 2020;16(4):90-101.
 60. Cazón P, Vázquez M. Applications of chitosan as food packaging materials. *Sustainable Agriculture Reviews* 36. Chapter-3. 2019;81-123.
 61. Carli CD, Aylanc V, Mouffok KM, Santamaria-Echart A, Barreiro F, Tomas A, Pereira C, Rodrigues P, Vilas-Boas M, Falcao SI. Production of chitosan-based biodegradable active films using bio-waste enriched with polyphenol propolis extract envisaging food packaging applications. *International Journal of Biological Macromolecules*. 2022;213:486–497.

62. Kumar N, Pratibha, Neeraj, Petkoska AT, AL-Hilifi SA, Fawole OA. Effect of Chitosan–Pullulan composite edible coating functionalized with pomegranate peel extract on the shelf life of mango (*Mangifera indica*). *Coatings*. 2021;11(764): 1-20.
63. Sree KP, Sree MS, Supriya P, Samreen. Application of chitosan edible coating for preservation of tomato. *International Journal of Chemical Studies*. 2020;8(4):3281-3285.
64. Prabha AR, Sivakumar K. Application of chitosan in food preservation. *International Journal of Science and Research (IJSR)*. 2015;6(7):2121-2128.
65. Jiang Z, Wang J, Xiang D, Zhang Z. Functional properties and preservative effect of p-hydroxybenzoic acid grafted chitosan films on fresh-cut jackfruit. *Foods*. 2022;11(1360):1-17.
66. Saputra D, Ula FR, Fadhila ABN, Sijabat YY, Romadoni AA, Windarto S. Nano-chitosan Spray as a preservative and food security of fishery products in the middle of the Covid-19 pandemic. *Jurnal Ilmiah Perikanan dan Kelautan*. 2022;14(1):71-82.
67. Kumar N, Pratibha Neeraj, Petkoska AT, AL-Hilifi SA, Fawole OA. Effect of chitosan–pullulan composite edible coating functionalized with pomegranate peel extract on the shelf life of mango (*Mangifera indica*). *Coatings*. 2021;11(764):1-20.
68. Kumar N, Neeraja Pratibha, Singla M. Enhancement of storage life and quality maintenance of litchi (*Litchi Chinensis* Sonn.) Fruit using chitosan:pullulan blend antimicrobial edible coating. *International Journal of Fruit Science*. 2020;20(3):1662–1680.
69. Hafsa J, Smacha MA, Charfeddinea B, Limema K, Majdoubb H, Rouatbi S. Antioxidant and antimicrobial proprieties of chitin and chitosan extracted from *Parapenaeus Longirostris* shrimp shell waste. *Annales Pharmaceutiques Françaises*. 2016;74:27-33.
70. Duan C, Meng X, Meng J, Khan IH, Dhai H, Khan A, Xingye AN, Zhang J, Tanzina H, Yonghao NI. Chitosan as A Preservative for Fruits and Vegetables: A Review on Chemistry and Antimicrobial Properties. *Journal of Bioresources and Bioproducts*. 2018;4(1): 11–21.
71. Călinoiu L, Ștefănescu BE, Pop ID, Muntean L, Vodnar DC. Chitosan Coating Applications in Probiotic Microencapsulation. *Coatings*. 2019;9 (194):1-21.
72. Chávarri M, Marañón I, Ares R, Ibáñez FC, Marzo F. del Carmen Villarán, M. Microencapsulation of a probiotic and prebiotic in alginate-chitosan capsules improves survival in simulated gastrointestinal conditions. *Int. J. Food Microbiol*. 2010;142:185–189.
73. Iyer C, Kailasapathy K. Effect of co-encapsulation of probiotics with prebiotics on increasing the viability of encapsulated bacteria under *In vitro* acidic and bile salt conditions and in yogurt. *J. Food Sci*; 2005.
74. Jiménez-Gómez CP, Cecilia JA. Chitosan: A Natural Biopolymer with a Wide and Varied Range of Applications. *Molecules*. 2020;25(3981):1-48.
75. Kahve HG, Duran A. The Use of Chitosan as Clarification Agent. *International Conference on Engineering and Natural Sciences*. 2016;2811-2814.

© Copyright (2024): Author(s). The licensee is the journal publisher. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:
The peer review history for this paper can be accessed here:
<https://www.sdiarticle5.com/review-history/117883>